



colorPol® IR 1550 BC4 T5 HT

Developed to match special needs of NIR applications between 1 480 nm and 1 650 nm. This polarizer utilizes dichroism of silver nanoparticles in glass to achieve superior contrast and durability.

Custom shapes, sizes and patterned structures are possible due to larger manufactured substrates. For assistance please contact your CODIXX Sales Engineer or one of the local distributors with your custom requirements.



Typical contrast (black) and transmittance (uncoated red, with AR-coating C1550 green) for un laminated parts



Typical contrast (black) and transmittance (uncoated red, with AR-coating C1550 green) for laminated parts

Key Benefits

- Transmittance typically greater than 97 % with antireflection (AR) coating
- Contrast ratio greater than 10,000 : 1
- Ideal for applications using the NIR wavelength ranges
- Customization
- Highly durable

Applications

- Free space isolators operating in C- and L-bands
- Optical communication
- LIDAR
- Polarization mode dispersion (PMD) measurement
- Molecular spectroscopic measurement
- NIR spectroscopy

Elliot Scientific Ltd.
 Unit 11 Sandridge Park, Porters Wood,
 St Albans, AL3 6PH, United Kingdom
 Tel: +44 (0)1582 766300
 Fax: +44 (0)1582 766340
 www.elliotscientific.com
 sales@elliotscientific.com

Specifications colorPol® IR 1550 BC4 T5 HT

	unlaminated	laminated
Spectral range	NIR	
Wavelength range with contrast > 10,000 : 1 ⁽¹⁾	1 480 to 1 650 nm	
Transmittance uncoated with AR-coating C1550 with 1 side AR-coating CS1550	> 88 % > 96 % > 92 %	> 87 % > 95 % > 91 %
Filter thickness ⁽²⁾	500 _{+20/-80} μm	1.7 ± 0.2 mm ⁽³⁾ 2.0 ± 0.2 mm ⁽⁴⁾
Acceptance angle (coating reference for 0°)	± 20°	
Accuracy of polarization axis to edge	< 0.5°	
Usual surface quality (MIL-O-13830A: Scratch / Dig) ⁽⁵⁾	40 / 20	
Operating temperature	-50 to +400 °C	-20 to +120 °C
Transmitted wavefront distortion at 633 nm over an inspection area of Ø10 mm	< 3 λ	< λ/4 ⁽⁴⁾
Recommended safe operation limit Laser damage threshold Continuous block Continuous pass Pulse peak power Equivalent pulse power density	10 W/cm ² 25 W/cm ² 12 MW/cm ² 1 μJ/cm ²	1 W/cm ² 5 W/cm ² 1 MW/cm ² 100 nJ/cm ²

⁽¹⁾ contrast: ratio of parallel to perpendicular transmittance
⁽²⁾ other thicknesses on request

⁽⁴⁾ laminated, ground and polished
⁽⁵⁾ other specifications available on request

Issued: 30/04/2018
Version: 1.01



Elliot Scientific Ltd.
Unit 11 Sandridge Park, Porters Wood,
St Albans, AL3 6PH, United Kingdom
Tel: +44 (0)1582 766300
Fax: +44 (0)1582 766340
www.elliotscientific.com
sales@elliotscientific.com

This document is for information purposes only. CODIXX AG reserves the right to change technical information without notice.